

WMP-VR

POLYPROPYLENE / SCRIM / KRAFT

Meets ASTM C1136, Type IV

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
White Film	Polypropylene	0.0015 inch	38.1 micron
Adhesive	Flame Resistant		
Reinforcing	Tri-directional	5 / inch (MD)	20 / 100 mm (MD)
	Fiberglass/Polyester	4 / inch (XD)	16 / 100 mm (XD)
Kraft	Natural	11 lbs / 3000 ft ²	18 gm / m ²

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	17 lbs / 1000 ft ²	83 gm / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.09 perm (grains/hrft ² in Hg)	5.17 ng / N's
Bursting Strength	ASTM D774	60 psi	4.2 kg / cm ²
Puncture Resistance	ASTM C1136	125 beach units	3.7 Joules
Tensile Strength	ASTM C1136	40 lbs/inch width (MD)	7.0 kn / m (MD)
		30 lbs/inch width (XD)	5.3 kn / m (XD)
Caliper / Thickness	Micrometer	0.008 inch	203 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion	No Corrosion
		No Delamination	No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Light Reflectance	ASTM C523	85%	85%

FIRE TESTING	UL 723		CAN ULC-S102M	
	Flame Spread	Smoke Developed	Flame Spread	Smoke Developed
Film Exposed	10	10	15	30
Kraft Exposed	15	5	15	45

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Lamtec Corporation Bartley-Chester Road P.O. Box 37 Flanders, New Jersey 07836-0037 USA
 (973) 584-5500 (800) 852-6832 Fax: (973) 584-5178