

ROCKWOOL Comfortboard® 110 is a rigid, high-density, non-combustible stone wool insulation board designed for use as an exterior continuous insulation in commercial applications.

Thermally efficient, moisture resistant and vapor permeable, Comfortboard® 110 is a non-structural external sheathing insulation that creates high-performance wall assemblies to improve the energy efficiency and fire resilience of buildings.

The vapor permeance of ROCKWOOL insulation allows for increased drying potential without trapping transient moisture in the assembly, reducing the risk of mold or corrosion of building components.

Comfortboard® 110 provides the rigidity and durability needed for many exterior cladding assemblies, such as metal and composite panel systems.

Learn more at rockwool.com





## Continuous Insulation

Board Insulation 05080\* Board Insulation 07 21 13\*\*

ROCKWOOL Comfortboard® 110 is a rigid mineral wool, non-structural insulated sheathing board used as continuous insulation in high-performance wall systems.

	Performance	Test Standard
Compliance	Mineral Fiber Block and Board Thermal Insulation - Type IVB Compliant Mineral Fibre Thermal Insulation for Buildings - Type 1 Compliant	ASTM C612 CAN/ULC S702
Reaction to Fire	Flame spread index = 0; Smoke developed index = 0 Flame spread index = 0; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114
Density	Actual Density - 11 lbs/ft³ (176 kg/m³)	ASTM C303
Corrosion Resistance	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel - Passed Corrosion of Steel - Passed Corrosion to Aluminum - Passed	ASTM C795 ASTM C665 ASTM C665
Thermal Resistance	R-Value / inch @ 75°F	ASTM C518 (C177)
Reaction to Moisture	Moisture Sorption - 0.28% Water Vapor Transmission, Desiccant Method - 2160ng/Pa.s.m² (35 perm) Water Absorption - 1.2% Determination of Fungi Resistance - Passed	ASTM C1104 ASTM E96 ASTM C209 ASTM C1338
Compressive Strength	584psf (28kPa) @ 10% compression 1566psf (75kPa) @ 25% compression	ASTM C165
Thickness Dimensions	1" (25.4 mm), 1.25" (32 mm), 1.5" (38.1 mm), 2" (50.8 mm), 2.5" (63.5 mm), 3" (76.2 mm), 4" (101.6 mm), 5" (127 mm)  24" x 48" (610 mm x 1219 mm), 48" x 72" (1219 mm x 1829 mm)	
Acoustical Performance	Thickness     125 Hz     250 Hz     500 Hz     1000 Hz     2000Hz     4000 Hz     NRC       1"     0.13     0.49     0.85     0.89     0.89     0.97     0.8       2"     0.5     0.71     0.85     0.9     0.96     1.01     0.85	ASTM C423

Issued 03-01-21 Supersedes 08-23-17 NOTE: \*Master Format 1995 Edition \*\*Master Format 2004 Edition. As ROCKWOOL has no control over installation design and workmanship, accessory materials or application conditions, ROCKWOOL does not warranty the performance or results of any installation containing ROCKWOOL's products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.



