

Spray Polyurethane Foam Insulation on Interior Surfaces of Metal Panels

Overview

This Technical Bulletin is intended to serve as a guide for the application of spray polyurethane foam insulation (SPF) used in metal panel assemblies. Single skin metal walls and roofs are durable and sustainable components of a building envelope system; however, the cladding offers no inherent insulation value to the building. To improve the energy efficiency of buildings, insulation, air barriers and vapor retarders are commonly used.

Metal panels with spray polyurethane foam insulation (SPF) are one method to insulate the building envelope. SPF on metal panels provide thermal insulating and air barrier capabilities as well as the ability to seal panel joints and act as a vapor barrier. This guide will outline the proper use and applications of SPF on metal panels.

SPF can be used to fill spaces in the panel assemblies and function as a key component of an air barrier system to minimize air leakage, however there are design parameters to be aware of when considering the use of SPF insulation for metal panels. MCA and the Spray Polyurethane Foam Alliance (SPFA) have conducted research on the installation of SPF onto steel and aluminum panels and have concluded the following best practice suggestions for SPF applied to the interior surface of metal panels:

- Closed-cell foam is recommended due to its water-resistant capabilities.
- SPF is a recognized insulation material to be used below and in contact with through-fastened metal roof assemblies.
- Using SPF below and in contact with standing seam metal roofs that are specifically designed for thermal expansion and contraction movement is discouraged due to the potential for restricting panel movement during temperature changes.
- The surface of the metal panel being sprayed should be free from moisture, lubricants, dirt or other contamination.
- The technique used to apply the SPF can affect the performance and appearance of the foamed panels (see page 2).
- Using a release fabric membrane between foam and a metal panel in a wall assembly is not recommended due to the potential of creating voids between the SPF and the panel.
- There is potential for stress-induced deformation (or “oil canning”) on 29 gauge or thinner material. (This can be minimized by following the foam manufacturers’ recommended application technique.)
- Always follow national and local code requirements for fire protection. Exposed SPF may require the use of an additional thermal barrier or other means for fire protection.
- Energy code compliance should be based on national and/or local code requirements for thermal performance.
- Inform electrical contractors of the use of SPF to prevent junction boxes from being covered.
- Inform HVAC contractors of the use of SPF to ensure that equipment is properly sized and that adequate make-up air is provided.
- Prevent SPF chemicals from being drawn into the ventilation system.
- Consider using a SPF contractor accredited by SPFA’s Professional Certification Program ⁽¹⁾

(compliant with ISO 17024) to provide high quality and safe installation of SPF insulation.

- Consult with the metal panel system manufacturer before applying SPF.

Discussion

Foam Insulation

SPF insulation is a chemical mixture of two components that are brought together using a spray gun. Mixing initiates polymerization through an exothermic reaction.

During curing, the foam may reach core temperatures as high as 325°F for short periods of time. Research suggests that during the curing process of closed cell SPF, the temperature of a metal panel in contact with the foam can increase in temperature as much as 80°F. Control of these temperature increases, and the potential deformation or oil canning of metal wall panels can be avoided utilizing SPFA installation guidelines.

Open-Cell and Closed-Cell Foam

There are two classes of SPF products: open cell and closed cell.

Open-cell SPF provides both insulation and the air sealing for the building assembly. The aged R value of open-cell SPF is approximately 3.5 Hr·ft²°F/btu per inch ⁽²⁾, however, the open cellular structure will permit water to migrate within the insulation and does little to restrict the movement of moisture vapor making it vapor permeable. With these limitations, open-cell foam is not recommended for applications where the foam is likely come into contact with water and an additional vapor retarder to control condensation may be required.

Closed-cell SPF insulation uses chemistry similar to open-cell SPF, however a different blowing agent is used to create the foam. The cellular structure is a series of adjoined closed cells, which holds the blowing agent gas, providing better insulation than

air. The closed-cell structure prevents the entry of water and reduces the movement of moisture vapor. Separate vapor retarders or water-resistant barriers are usually not necessary. Closed-cell SPF typically has a permeability less than 1 perm when applied at 2” thickness and an aged R value of 6 or 7 hr·ft²°F/Btu per inch ⁽²⁾. Closed-cell spray foam insulation is the more commonly used type of SPF applied on metal panels.

Application Technique

It is important that SPF is **applied by a certified foam spray technician** in order to apply the required insulation thickness to achieve the optimum insulation density, adhesion, and thickness. The recommended application approach is to spray the foam in controlled thickness with a “picture frame” technique. SPFA describes this picture framing motion in which the applicator surrounds the interior perimeter of the wall framing stud, allowing the foam to rise along the stud. ⁽³⁾ This technique can also help to prevent SPF from getting between girts and architectural metal wall panels which could cause metal deformation.

The thickness of the initial pass fillet during picture framing should be at least 0.5” and should not exceed the maximum pass thickness recommended by the foam manufacturer. The minimum thickness of the initial pass is specified to provide enough material to activate the blowing agent and initiate the cure. ⁽⁴⁾ After picture framing the perimeter of the area, the applicator fills in the center of the cavity using the maximum thickness recommended by the foam manufacturer. Maximum pass thickness varies by foam formulation and is listed in the technical data for each SPF product. Excessive pass thickness can result in poor quality by elevating the foam temperature beyond acceptable limits during cure. For most closed-cell SPF, the maximum pass thickness is 1.5 to 2”. It is important for applicators of closed-cell SPF to

follow manufacturers' installation instructions on pass thickness limits and proper cooling times between subsequent passes made to develop the desired total thickness of the insulation.



Photo of SPF being applied to wood deck using picture framing technique. Spraying foam onto a metal panel surface would be done in the same fashion. (Courtesy of Spray Foam Professional Magazine)

Installers are trained to check the substrate surface for moisture, dirt, oils, rust or other conditions that can interfere with proper foam adhesion. The surface should be cleaned of these contaminants prior to spraying the insulation. Adhesion to the metal surface can be determined onsite using a pull-tester (ASTM D 4541 Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers).

Some SPF contractors use a release material such as building wrap or fabric to allow for easier replacement of damaged panels, however the use of a release material poses the potential of creating air gaps between the back of the SPF foam and the metal panel. These gaps could allow condensation to accumulate between the SPF and the panel and framing members.

Blown In Blanket System (BIBS) non-woven fabric systems were evaluated by MCA to determine if SPF would adhere properly while allowing for easier metal panel disassembly. Results suggest the SPF had good adhesion with the BIBS membrane and would allow easier replacement of metal panels, however it can be difficult to install

SPF directly onto the light-weight BIBS fabric in windy conditions. MCA research suggests the BIBS fabric is no better than SPF applied directly onto the metal panels in terms of appearance of the panels.

Paint Performance

A long-term investigation was done to assess the impact of SPF insulation on the performance of paint systems used on the exterior surface of insulated pre-painted metal panels using the same metrics as typical finish warranties. The assertion was that darker panels subjected to high solar gain would develop higher surface temperatures due to the SPF insulation reducing heat flow to the cooler, unexposed side of the assembly, possibly effecting paint performance.

Samples from the mocked-up assemblies created for the subject study painted brown and dark bronze, were exposed at a Cool Roof Rating Council (CRRCC) accredited manufacturer test laboratory and test farm in South Florida. Half of the samples were exposed vertically, and half were exposed at a 45° angle from horizontal. After 7 years of exposure, the samples were evaluated for chalking, gloss retention and color change. Results are shown in Table 1. Generally, the presence of the SPF had little effect on the chalk rating, although it did increase (worsen) by a single unit in one case. Interestingly, the SPF-backed samples had improved gloss retention and less color change in every case.

The test methods used to evaluate the samples are given in the footnotes of Table 1, but some additional explanation on color change is warranted. Color is evaluated initially and after exposure using Hunter L-a-b color space values. This methodology expresses color as three independent values of lightness (L), red-green tint (a) and blue-yellow tint (b)⁽⁵⁾. This scale can be visualized as a 3-dimensional space shown in Figure 1.

Table 1: Exposure Study Results

Color	Exposure Angle	Backer	Chalk Rating ¹	Retained Gloss ²		Color Change ³				Comparisons		
				Initial Gloss	Exposed Gloss	ΔL	Δa	Δb	ΔE	Chalk Rating	Retained Gloss	Color Change
Dark Bronze	45°	None	6	25.7	0.5	7.27	-0.97	-0.31	7.34	0.0%	120.0%	-0.8%
		SPF	6	25.7	1.1	7.22	-0.86	-0.52	7.28			
	90°	None	8	25.7	3.6	4.38	-0.65	-0.49	4.45	0.0%	83.3%	-40.9%
		SPF	8	25.7	6.6	2.6	-0.35	-0.28	2.63			
Brown	45°	None	5	26.5	1.7	6.51	-1.74	-1.54	6.91	20.0%	41.2%	-10.7%
		SPF	6	26.5	2.4	5.81	-1.42	-1.52	6.17			
	90°	None	8	26.5	10.7	2.46	-0.67	-0.71	2.64	0.0%	22.4%	-12.1%
		SPF	8	26.5	13.1	2.18	-0.57	-0.58	2.32			

Table Notes:

1. Chalk rating determined by ASTM D4214.
2. Gloss measurements determined by ASTM D523.
3. Color measurements determined by ASTM D2244.

When using the Hunter L-a-b scale, it is common to express color change as a vector sum of the L, a, and b value, called “Delta E” (ΔE).



Figure 1: Hunter Lab Color Space

Inspection

It is recommended that a building owner periodically inspect a metal assembly for potential leaks. Visual detection of leaks, in general, may be more difficult with the use of SPF. Undetected leaks can potentially cause accelerated panel corrosion.

Conclusions

The metal panel manufacturer should be consulted when considering using SPF on the underside of standing seam metal roofing due to the possibility of restricting thermal movement of the panels.

Closed-cell Spray Polyurethane Foam is a viable insulation material for the interior surfaces of steel and aluminum metal wall panels and through-fastened roof assemblies.

Possible deformation, distortion, or oil canning caused by the application of SPF depends on the installation conditions, installation application methods, proper product selection, and applicator training.

SPFA-PCP accredited contractors and certified installers familiar with SPFA guidelines have access to SPFA resources.

References

1. Spray Polyurethane Foam Alliance Professional Certification Program (SPFA-PCP) for individual installer certification and contractor/supplier accreditation.
2. Spray Polyurethane Foam Alliance

3. Tech Tip: SPF Picture Framing Technique, Spray Polyurethane Foam Alliance, 2010
4. Tech Tip: Spray Polyurethane Foam – Exotherm vs. Thickness, Spray Polyurethane Foam Alliance, 2010
5. Measuring Color using Hunter L, a, b versus CIE 1976 L*a*b. Hunter Application Note 1005.000. Hunter Associated Laboratory (2012)

Acknowledgements

The MCA thanks member companies MBCI for the contribution of materials and labor to construct the full-size roof and wall assemblies and Sherwin-Williams for use of their test farm and laboratory.

The MCA also thanks the Spray Polyurethane Foam Alliance (SPFA) for their involvement in the research and their contribution to this Technical Bulletin. For more information visit www.sprayfoam.org.

Founded in 1983, the Metal Construction Association brings together the diverse metal construction industry for the purpose of expanding the use of all metals used in construction. MCA promotes the benefits of metal in construction through:

- Technical guidance
- Product certification
- Educational and awareness programs
- Advocating for the interests of our industry
- Recognition of industry-achievement awards
- Monitoring of industry issues, such as codes and standards
- Research to develop improved metal construction products
- Promotional and marketing support for the metal construction industry
- Publications to promote use of metal wall and roof products in construction

For more information, please visit the MCA Web site at www.metalconstruction.org

Copyright © 2023 Metal Construction Association. All rights reserved.

No part of this publication may be reproduced in any form or by any means, including photocopying, or utilized by any information storage or retrieval system without permission of the copyright owner.

This bulletin is for general information only. The bulletin is designed to delineate areas requiring consideration. Information contained in the bulletin should not be used without first securing competent advice with respect to its suitability for any given application. MCA does not assume responsibility and disclaims any representation or warranty, express or implied, that such information is suitable for any general or particular use. Anyone making use of the bulletin assumes all liability resulting from such use.

The existence of the bulletin does not in any respect preclude a member or nonmember of MCA from manufacturing, selling, or specifying products not conforming to the bulletin, nor does the existence of an MCA bulletin preclude its voluntary use by persons other than MCA members. The bulletin does not purport to address all safety problems associated with its use or all applicable regulatory requirements. It is the responsibility of the user of the guideline to establish appropriate safety and health practices and to determine the applicability of regulatory limitations before use of the bulletin.

The Metal Construction Association reserves the right to change, revise, add to, or delete any data contained in the bulletin without prior notice.

It is the responsibility of the end user to verify the applicability of this information with the local building and fire officials.